

PSX® 700

DESCRIPTION

Two-component, engineered siloxane coating

PRINCIPAL CHARACTERISTICS

- Unique, high gloss, engineered siloxane
- Can be applied directly over inorganic zinc
- Excellent color and gloss retention
- High solids, VOC compliant
- Applied by brush, roller or spray, without thinning
- Good resistance to splash- and spillage of chemicals

COLOR AND GLOSS LEVEL

- Full color range
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.3 lb/US gal)
Volume solids	90 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 119.0 g/kg max. 164.0 g/l (approx. 1.4 lb/US gal) EPA Method 24: 0.7 lb/US gal (84.0 g/l)
Recommended dry film thickness	75 - 175 µm (3.0 - 7.0 mils) per coat
Theoretical spreading rate	7.2 m ² /l for 125 µm (289 ft ² /US gal for 5.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 3 hours Maximum: Unlimited
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



PSX® 700

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Compatible previous coat must be dry and free from any contamination
 - Aged suitable coating must be dry and free from any contamination
 - Aged coatings may require abrading prior to applying this product
 - Prepare damaged areas to original surface preparation specifications, feathering edges of intact coating
 - For touch-up and repair; apply additional material after removing dirt, contaminants and old loose coatings or antifoulings
-

Substrate temperature

- Substrate temperature during application and curing should be above 0°C (32°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Relative humidity during application and curing should be above 40% to obtain optimal curing properties
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- Use a power mixer powered by an air- or explosion-proof electric motor
-

Induction time

None

Pot life

4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Airless spray

Recommended thinner

THINNER 60-12 or THINNER 21-06

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Brush/roller

- The recommended DFT cannot be reached in one coat
 - Natural bristle
 - Maintain a wet edge
 - Level any air bubbles with a bristle brush
-

PSX® 700

Cleaning solvent

THINNER 90-58

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	12.0 m ² /l (481 ft ² /US gal)
125 µm (5.0 mils)	7.2 m ² /l (289 ft ² /US gal)
175 µm (7.0 mils)	5.1 m ² /l (206 ft ² /US gal)

Overcoating interval for DFT up to 175 µm (7.0 mils) at RH 40% or above					
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	12 hours	7 hours	3 hours	2 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited

Notes:

- Surface should be dry and free from any contamination before recoating
- Please contact your PPG representative for more details

Curing time for DFT up to 175 µm (7.0 mils)		
Substrate temperature	Dry to touch	Dry to handle
5°C (41°F)	7 hours	16 hours
10°C (50°F)	4.5 hours	8.5 hours
20°C (68°F)	2 hours	4.5 hours
30°C (86°F)	1 hour	3 hours

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6.5 hours
20°C (68°F)	4 hours
30°C (86°F)	1.5 hours

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets

PSX® 700

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• SURFACE PREPARATION OF CONCRETE (FLOORS)	INFORMATION SHEET	1496
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650
• PSX® 700 SILOXANE QUALITY ASPECT APPLICATION	INFORMATION SHEET	1721

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



**PPG Protective &
Marine Coatings**

Bringing innovation to the surface.™